

## TECHNICAL SPECIFICATIONS

Poly propylene in reels 120 mm :

1 -Description And Using : impermeable Poly propylene in bobbins are used for Wrapping hard pack on GD Machines model C600-C800 .

2 - Width : 120 mm.

3 - Internal bobbin diameter : 76 mm  $\pm$  0.5 mm .

4 - Length: 3000 m.

5- Grammage : ( 16 -23 ) g/m<sup>2</sup>

6 - Thickness : ( 18 -25 )  $\mu$ m

7 - Glossing : 60 % min

8 - Milting point : ( 160 - 166 ) C<sup>o</sup>

9 - Tension strength : 1.5 kg/15 mm min

10 - Upon the samples evaluation , the following issues should be taken into consideration: strength , continuity , curving , adherence to tear tape , good bobbin winding , suitability on the machines till bobbins end , strength of the inner core .

### Packing :

-The bobbins should be placed on wooden pallets and supported from the bottom with a strong wooden base which can be used with fork-lifts . The pallet is packed and strapped according to the international standards .

The required samples : /5/ bobbins

## ات الفنية

ي بروبيلين قياس ١٢٠ مم

ف و الاستعمال : بكر بولي بروبيلين كتيم يستعمل كينات الكرتون على آلات G.D طراز C600-C800

ض ١٢٠ مم

ر الداخلي ٧٦ مم  $\pm$  ٠,٥ مم

يل ٣٠٠٠ م

إماج : ( ١٦ - ٢٣ ) غ/م<sup>٢</sup>

ماكة : ( ١٨ - ٢٥ )  $\mu$ m

سقل : ٦٠ % اصغري

رجة الاتصهار : ( ١٦٠ - ١٦٦ ) م<sup>o</sup>

رة الشد : ١,٥ كغ/١٥ مم اصغري

يؤخذ بعين الاعتبار عند تقييم النماذج البنود التالية :

ثانة - الاستمرارية - الالتواء - الالتصاق مع شريط

زيق - جودة لف البكرة - الملازمة على الآلات حتى نهاية

كرة - متانة الاسطوانة الداخلية .

### ف :

ضع البكرات على طبالي خشبية مدعمة من الأسفل بقاعدة

جيدة متينة صالحة للاستعمال مع الروافع الشوكية

ف الطبالية وتحزم حسب المواصفات العالمية .

مأذج المطلوبة : / ٥ / بكره

تمد المواصفة الفنية للمناقصة رقم : ٢٠٢١/٦٣

المدير العام

محسن حسن عبيدو